

# CARBON PIPES FOR LOW TEMPERATURES

## ASTM A333 - ASME SA333

Seamless and welded pipes

---

**USE** Conveying fluids at low temperatures

**STEEL GRADE** 6

**PROCESSING** ► Seamless  
► Welded

**TOLERANCES** **THICKNESS**  
+ not specified (delimited by mass) / – 12,5%

### OUTSIDE DIAMETER

Diameter (mm)	Tolerance (mm)
10,3 < D ≤ 48,3	+0,4 / -0,8
48,3 < D ≤ 114,3	+0,8 / -0,8
114,3 < D ≤ 219,1	+1,6 / -0,8
219,1 < D ≤ 457	+2,4 / -0,8
457 < D ≤ 660	+3,2 / -0,8
660 < D ≤ 864	+4,0 / -0,8
864 < D ≤ 1219	+4,8 / -0,8

### OUT OF ROUNDNESS

Within the limits of tolerance for the diameter

### MASS

The mass per unit of length for pipes ≤ 323,8mm must not vary by + 10% / – 3,5% from the values specified

For pipes > 323,8mm the mass per unit of length must not vary by + 10% / – 5% from the values specified

The benchmark parameters must be identified in the ANSI B36.10 and ANSI B36.19 standards and for non-standardized sizes the following equation must be applied:

$$M = t(D - t) \times C$$

Any restrictions are shown in the standard

### STRAIGHTNESS

- Reasonably straight

# CARBON PIPES FOR LOW TEMPERATURES

## ASTM A333 - ASME SA333

*Seamless and welded pipes*

---

### MARKING

Pipes with  $D \leq 48,3\text{mm}$  will be identified by means of a label applied to one end of the bundle

Pipes with  $D > 48,3\text{mm}$  will be marked legibly 300mm from one end with the following information:

- Manufacturer's name or trademark
- Reference standard
- Steel grade
- Cast number
- Resilience test performance temperature
- Diameter and thickness
- Length
- Weight
- Any additional instructions

### CERTIFICATION

UNI EN 10204

### SIZE

### RANGE

ASME B36.10